



Europäisches  
Patentamt

European  
Patent Office

Office européen  
des brevets

25. 11. 2004

Bescheinigung


Certificate

Attestation

Die angehefteten Unterlagen stimmen mit der ursprünglich eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.


The attached documents are exact copies of the European patent application described on the following page, as originally filed.

Les documents fixés à cette attestation sont conformes à la version initialement déposée de la demande de brevet européen spécifiée à la page suivante.



Patentanmeldung Nr. Patent application No. Demande de brevet n°

03293199.0



Der Präsident des Europäischen Patentamts;  
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets  
p.o.

R C van Dijk

BEST AVAILABLE COPY



Anmeldung Nr:  
Application no.: 03293199.0  
Demande no:

Anmeldetag:  
Date of filing: 17.12.03  
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

Tarkett s.a.s.  
2, rue de l'Egalité  
92748 Nanterre Cedex  
FRANCE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:  
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.  
If no title is shown please refer to the description.  
Si aucun titre n'est indiqué se referer à la description.)

Electrically conductive floor coverings

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s)  
revendiquée(s)  
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/  
Classification internationale des brevets:

C09D5/00

Am Anmeldetag benannte Vertragsstaaten/Contracting states designated at date of  
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LU MC NL  
PT RO SE SI SK TR LI

P-TARKETT-019/EP

1

## ELECTRICALLY CONDUCTIVE FLOOR COVERINGS

### *Field of the Invention*

The invention relates to an electrically conductive floor covering.

### *Description of the-Related Art*

Static charges, which are produced by walking or travelling on plastic floor coverings, particularly at low atmospheric humidity, represent a serious problem, particularly for sensitive electronic components. The electronic components may be damaged or their function may be impaired by electrostatic discharges. Furthermore, in areas in which easily flammable materials are worked with, there is the danger that these materials will be ignited by spark-over in the event of static discharges. The avoidance of static charges is particularly important in surroundings which are air-conditioned and therefore have a low atmospheric humidity, such as computer centers, manufacturing facilities for electronic components and electronic devices, radiological facilities, operating rooms, and other areas in which care is taken to provide an atmosphere low in dust and particles.

The floor coverings typically used, for example those based on polyvinyl chloride or rubber mixtures, are insulators. They may be made conductive if conductive fillers or antistatic agents are mixed in. However, a relatively large quantity, typically between 30 and 50 volume-percent of a conductive filler, must be used to achieve a sufficient conductivity. Metallic materials, conductive carbon black, or graphite are used in particular as conductive fillers, but the use of the necessary quantities results in black or gray products. If antistatic agents are used, there is the disadvantage that these materials react very strongly to changes in atmospheric humidity and their effectiveness is therefore strongly dependent on the environmental conditions.

A method for producing highly compressed, conductive covering material from thermoplastic plastics is known from European Patent A 869 217, in which particles of the thermoplastic plastic, which are provided with a coating

containing a conductive substance, are compressed under elevated temperature and high pressure into a block with conductive paths and subsequently split transversely to the direction of the conductive paths into slabs of the desired thickness, with these slabs having conductive paths in the direction of their thickness. In this way, light-colored, conductive floor coverings made of thermoplastic plastic are obtained.

Polyurethane (PU) and other top coatings such as PU acrylates, epoxy acrylates, polyester acrylates, polyether acrylates, silicone acrylates etc are widely used as surface reinforcement on plastic floorings, for residential use as well as for commercial use. These top coatings make the surface of the floor covering smoother, decrease the friction and because of that improve the cleaning and maintenance properties.

One disadvantage with the existing top coatings is their electrical insulation properties that make them unsuitable for conductive homogeneous floorings.

Conductive floorings should have an electrical resistance between 0,01 and 1,0 M $\Omega$  during the entire product lifetime. To reach this goal, the top coating should not have any or very low influence on the total conductivity of the flooring. The conductivity of the flooring should be determined by the amount and quality of conductive material in the substrate, for example by the carbon black (black spots) integrated into the substrate.

For a conductive floor covering the electrical resistance according to EN 1081 will increase from approx. 0,05-0,1 M $\Omega$  to more than 100 M $\Omega$  when a traditional top coating is applied. The height of the increase depends on thickness, the nature and grade of the top coating used.

The use of chemical additives to lower the electrical resistance is well known, but is not suitable for floorings because the resulting top coatings show low stain resistance, a risk for migration of the additives in some cases and because the conductivity obtained is not stable in time. Often these chemicals also decrease the transparency and/or give a colour to the top coating.

Mineral materials or conductive pigments can also be used to lower electrical resistance, but they have generally a colouring effect on the coating.

### **SUMMARY OF THE INVENTION**

In accordance with the present invention, a surface covering comprising substrate and a surface or top coating is provided for conductive flooring with a top coating exhibiting improved cleaning and maintenance properties as well as good transparency.

Accordingly the invention provides a new and improved surface covering comprising a substrate and a top coating characterised in that the top coating comprises particles with a conductive coating having a mean particle size (numbers) between 0.1 and 50  $\mu\text{m}$ .

The conductive flooring with a top coating according to the invention exhibits improved cleaning and maintenance properties as well as an increase in transparency. Furthermore the conductivity of the flooring remains constant during its entire lifetime.

According to a preferred embodiment, the particles are substantially spherical. Such spherical particles are more easily mixed with the top coating before the application of said top coating to the substrate.

The particles preferably comprise a coating of silver, aluminium, copper, nickel, gold or an alloy thereof with another metal. Metal-coated spherical beads are especially preferred. Such a metal coating gives very good performances and allows to effectively lead any charges accumulating in the top coating down the substrate through which they are then lead to the ground.

The particles or the metal-coated spherical beads have a dry bulk resistivity of advantageously between 0.0001 and 0.01 Ohms/cm. Very good results are achieved with metal-coated spherical beads having a dry bulk resistivity of about 0.001 Ohms/cm.

The top coating comprises – in a preferred embodiment – between 0.01 and

10% w/w of particles based on the weight of the top coating. The optimal ratio depends mainly on the type and on the thickness of top coating material used.

The top coating comprises preferably a PU-dispersion (like Neovez R988 of Neokesins), a PU-solution, a 2-components PU, a PU acrylate (like 5 Aqualux 1420-8500 from Teknos A/S), an epoxy acrylate, a polyester acrylate, a polyether acrylate, a silicone acrylate or a mixture thereof.

The coating comprises an urethane derived polymer preferably polyurethane and most preferably a water based UV-curable PU-acrylate dispersion with a dry content of between 5% and 80% w/w preferably 20 and 60 % w/w. Such top 10 coatings are widely used in the art for applications where an electrical conductivity is not required.

The top coating normally has a thickness of between 0,5  $\mu\text{m}$  to 100  $\mu\text{m}$ .

The top coating may be applied by any known technique like roller coating, reverse and inreverse, spraying, curtain, screen etc.

15 Of course, the size of the particles with a conductive coating thickness depends on the thickness of the top coating. As a general rule, the mean size of the particles should be not be more than about half of the thickness of the top coating.

The above described top coating may be used on any a conductive and 20 antistatic flooring, preferably on a PVC based flooring with vertical conductive channels, containing carbon black. Such a product is commercially available from the Tarkett AB under the trademark TORO EL. Polyolefin or rubber based floors may also be used.

#### **DETAILED DESCRIPTION OF A PREFERRED EMBODIMENTS**

The present invention will be described in more detail in the following 25 with reference to the example

**Example1**

In order to produce a conductive flooring the following materials were used:

1) Conductive silver glass spheres (CSGS 10 A, available from Progressive Fillers Int'l Inc. of Tennessee, USA) having a mean particle size of 10  $\mu\text{m}$ , pure silver plating of 12% and a dry bulk resistivity of 0.001 Ohms/cm

2) Top coat: Aqualux™ from Teknos A/S Denmark, a water base UV-curable PU-acrylate dispersion with a dry content of approx. 40 %.

3) Plastic flooring of PVC (Toro EL available from Tarkett AB Sweden) with "vertical conductive channels" containing carbon black.

About 1 % w/w of CSGS 10A were mixed in the above mentioned PU acrylate dispersion and the conductive flooring were coated with approx 20 g/m<sup>2</sup> in a roller coating station.

The "film" thickness of the top coating after drying was about 8  $\mu\text{m}$ .

Two control samples were used to compare the results one without any top coating and an other one with the same top coating but without any conductive particles.

Since only approx. 1 % of CSGS 10A particles were used the top coating is transparent. The CSGS 10A particles give no or very little visible change of the surface. The rather low content of spheres implies also that the top coat only is conductive in the vertical direction from the surface to the conductive substrate and not in the horizontal direction.

The properties of the flooring were determined according to the following methods

1) European Standard EN 1081 (January 1998) : Resilient floor coverings-Determination of the electrical resistance.

2) ESD association standard (ANSI/ESDS7.1-1994) )

It was found that the electrical resistance of the conductive flooring

(Toro EL) without top coat was between 0,03- 0,1 M $\Omega$  , whereas the electrical resistance of the conductive flooring (Toro EL) with PU coating without CSGS was >500 M $\Omega$ . The electrical resistance of conductive flooring (Toro EL) with conductive PU according to the invention was 0,05- 0,2 M $\Omega$ .

- 5                    No colour change was noticed using the above concentration of particles, no dependency on air humidity and a very high vertical conductivity through the top coating according to the invention to the conductive parts (carbon black) in the substrate. This top coating does not increase the electrical resistance of the flooring significantly. The resistance of the substrate beneath the PU top coat
- 10 determines the flooring conductivity. Since a "normal" amount of PU was used, the flooring cleaning properties were very much improved compared to the reference without PU.



P-TARKETT-019/EP

7

### Claims

1. A surface covering comprising a substrate and a top coating characterised in that the top coating comprises particles with a conductive coating having a mean size between 0.1 and 50  $\mu\text{m}$ .
- 5 2. The surface covering according to claim 1, wherein the particles are substantially spherical.
3. The surface covering according to claim 1 or 2, wherein the particles comprise a coating of silver, aluminum, copper, nickel, gold or an alloy thereof with another metals.
- 10 4. The surface covering according to any of the preceding claims, wherein the particles have a dry bulk resistivity of between 0.0001 and 0.01 Ohms/cm.
5. The surface covering according to any of the preceding claims, wherein the top coating comprises between 0.01 and 10% w/w of particles based on the weight of the top coating.
- 15 6. The surface covering according to any of the preceding claims, wherein the top coating comprises a PU-dispersion, a PU-solution, a 2-components PU, a PU acrylate, an epoxy acrylate, a polyester acrylate, a polyether acrylate, a silicone acrylate or a mixture thereof
- 20 7. The surface covering of claim 5, wherein the coating comprises an urethane derived polymer preferably polyurethane.
8. The surface covering of claim 5, wherein the coating comprises a water based UV-curable PU-acrylate dispersion with a dry content of between 5 % and 80% w/w , preferably between 20 and 60 % w/w.

*P-TARKETT-019/EP*

8

9. The surface covering according to any of the preceding claims, wherein the top coating has a thickness of between 0,5  $\mu\text{m}$  to 100  $\mu\text{m}$
10. The surface covering according to any of the preceding claims, wherein the substrate is a conductive and antistatic flooring.
- 5 11. The surface covering according to any of the preceding claims, wherein the substrate is a PVC, polyolefin or rubber based flooring with vertical conductive channels.

*P-TARKETT-019/EP*

9

# **ABSTRACT**

A surface covering comprising a substrate and a top coating characterised in that the top coating comprises particles with a conductive coating having mean size between 0.1 and 50  $\mu\text{m}$ .

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**